



شرکت دارویی ره آورد تأمین (سهامی عام)
برگه استعلام کتبی

شماره: ۱
تاریخ: ۱۴۰۴/۱۱/۰۷

با سلام و احترام

این شرکت در نظر دارد جهت خرید لوازم یا خدمات مورد نیاز خود به شرح ذیل اقدام نماید. لذا خواهشمند است قیمت پیشنهادی خود را در مقابل اجناس قید شده اعلام و در خاتمه آدرس و تلفن و مهر امضاء را منظور فرمائید.

تلفن: ۷ - ۴۴۹۹۱۳۳۵ / داخلی ۲۲۳

فکس: ۴۴۹۹۰۵۸۲

همراه: نبی زاده ۰۹۹۱۰۷۰۴۶۲۵

ایمیل:

ردیف	نام کالا	مشخصات فنی / ابعاد	تعداد	قیمت (ریال)	قیمت کل (ریال)	شماره درخ
۱	اچ پی ام سی ۶ (Hydroxy Propyl Methyl Cellulose 6 cps)	HPMC6-Cas No: 9004-65-3	۴۰۰۰ کیلوگرم			۱۶۲
۲						
۳						
۴						
۵						
				نام و امضاء استعلام گیرنده:		

توزیع نسخ: ۱- مالی

مهر و نوشت (Transcript)	شماره بازنگری: ۰۱	تاریخ بازنگری: ۱۴۰۳/۰۹/۰۶	تاریخ تالیف: ۱۴۰۲/۰۹/۲۰	کد فرم: FM-563-01
	صفحه ۱ از ۱	تاریخ اعتبار: ۱۴۰۷/۰۹/۰۷	تاریخ اجرا: ۱۴۰۳/۰۹/۰۷	کد SOP مربوطه: QC-226

Item Name : Hydroxypropyl Methylcellulose 6 cP (Hypromellose)	Brand Name : -
Item Code : 21500037	CAS No. : 9004-65-3
SOP for Analysis : QC-563	Precaution : MSDS (MD-119)
Storage Conditions : Preserve in well-closed containers. No storage requirements are specified.	Shelf Life: At Least 2 Years

No.	Tests	Specifications	Reference
1	Description	White to slightly off-white, fibrous or granular powder.	USP46-NF41
2	Solubility	Swells in water and produces a clear to opalescent, viscous, colloidal mixture. Insoluble in dehydrated alcohol, in ether, and in chloroform	USP46-NF41
3	Identification	A The powdered material aggregates on the surface.	USP46-NF41
		B A slurry is formed, but the powdered material does not dissolve. Cool the slurry to 10°, and stir using a magnetic stirrer. The resulting liquid is a clear or slightly turbid solution with thickness dependent on the viscosity grade.	
		C A red color develops at first that changes to purple within 100 min	
		D A coherent, clear film forms on the glass slide	USP46-NF41
		E The flocculation temperature is higher than 50°.	
4	Loss on drying	Max. 5.0 %	USP46-NF41
5	Residue on ignition	Max. 1.5 %	USP46-NF41
6	Methoxy Content	28.0 - 30.0 %	USP46-NF41
7	Hydroxypropoxy Content	7.0 - 12.0 %	USP46-NF41
8	pH	5.0 - 8.0	USP46-NF41
9	Viscosity	4.8 - 7.2 cP	USP46-NF41

Comments:

Preparation By:
N. Soleymani

Checked By:
M. Keshvari

Approved By:
Y. Khandan